

Doc. no. D.2918.Q
Rev. 1
Release date: 16-08-2021
Author: BEL
Approved by: NBO

Block Foam PUR 80

Rigid PUR 80 kg/m³ is produced with pentane.
Typical data for the system as below.

Properties	Value	Unit	Standard
Density	72-88	[g/l]	EN1602
Compressive Strength	> 600	[kPa]	EN826
E-Modulus	> 20	[MPa]	-
Tensile Strength	> 650	[kPa]	EN1607
E-Modulus	> 19	[MPa]	-
Bending Strength	> 900	[kPa]	EN12089
E-Modulus	> 17	[MPa]	-
Closed cells	> 90	[%]	ISO4590

Notice

Data given is not a specification for the product, only typical values. All statements, information's and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty or responsibility of any kind expressed or implied.